



MICRO POWDERS, INC.
High Performance Wax Additives

Architectural Coatings

The performance demands of today's modern interior and exterior architectural coatings can be achieved with a wax additive that provides effective gloss control, enhanced burnish resistance, improved soil release, and superior in-can stability. Micro Powders' products can enhance these properties while also improving water repellency, scratch resistance and adding a smooth surface feel.

Recommended Products Typical Properties

(Selector Guide on reverse side)

Product	Melt Point (°C)	Density (g/cc@25°C)	Mean Particle Size (µm)	Max. Particle Size (µm)
AquaBead 519	126 - 132	0.94	6.0 - 8.0	22.00
AquaBead 525E	60	1.00	Sub-micron aqueous emulsion	
AquaKlean 403	120	1.00	Sub-micron aqueous emulsion	
AquaMatte 22	135 - 140	0.99	6.0 - 8.0	22.00
AquaMatte 31	135 - 140	0.99	8.0 - 12.0	31.00
AquaPoly 215	105 - 111	0.94	9.0 - 11.0	31.00
AquaPolyfluo 411	117 - 123	1.02	6.0 - 8.0	22.00
Aquawax 214VF	98 - 102	0.96	5.0 - 7.5	22.00
MicroMatte 1213 UVW	150 - 156	1.07	5.0 - 7.5	22.00
Micropro 400	140 - 143	0.94	4.5 - 7.5	22.00
MicroTouch Series	N/A	1.05	Available from 5 µm - 35 µm mean	
MP-22XF	102 - 106	0.93	5.0 - 6.0	22.00
MPP-123AL	110 - 113	0.97	9.5 - 12.5	31.00
NatureFine R331	77 - 82	0.96	6.0 - 10.0	31.00
NatureMatte 31	170 - 180	1.25	7.5 - 10.5	31.00
Polyfluo 190	121 - 132	0.98	9.0 - 12.0	31.00
Polyfluo 900	121 - 132	1.02	9.0 - 12.0	31.00
PropylMatte 31	160 - 170	0.89	8.0 - 12.0	31.00
PropylMatte 31HD	160 - 170	1.07	8.0 - 12.0	31.00
PropylMatte 31SA	160 - 170	1.02	8.0 - 12.0	31.00
PropylTex Series	160 - 170	0.89	Wide range available (14 mesh - 325 mesh)	
PropylTex HD Series	160 - 170	1.07	Wide range available (200 mesh - 325 mesh)	
SuperGlide 904	138 - 145	0.96	4.0 - 6.0	22.00
Synfluo 172VF	104 - 110	0.97	4.0 - 7.0	22.00

Architectural Coatings Selector Guide

● Extremely Effective
 ◐ Very Effective
 ○ Effective
◆ Available as a Waterborne Dispersion

Product	Description	Suggested Use Level	Recommended System Type*	Interior/ Exterior	Burnish Resistance	Mating and Gloss Control	Block Resistance	Resistance to Dirt Pick Up	Cleanability	Water Repellency/Beading	Scratch and Mar Resistance	Texture	Lubricity and Smooth Feel	Soft Touch	Heel Mark Resistance	Non-Skid	Film Clarity	In-Can Stability	Gloss Retention	Biodegradable
◆ AquaBead 519	Hydrophobically modified synthetic wax	1.0 - 4.0%	S	E			○	◐	○	●										
AquaBead 525E	Paraffin/carnauba wax emulsion	2.0 - 10.0%	W	E				◐	○	●							◐		◐	
AquaKlean 403	Polyethylene/paraffin wax emulsion	3.0 - 10.0%	W	I,E	○		◐	◐	●	●							●		●	
◆ AquaMatte 22	Oxidized polyethylene	2.0 - 5.0%	W	I,E	◐	◐	○		●		●		◐	○					●	
◆ AquaMatte 31	Oxidized polyethylene	2.0 - 5.0%	W	I,E	◐	●	○		◐		●		◐	○					●	
◆ AquaPoly 215	Oxidized polyethylene	1.0 - 2.0%	W	I			◐		○		◐		○							
◆ AquaPolyfluo 411	Modified oxidized polyethylene/PTFE	0.5 - 2.0%	W	I,E	○		●	○	◐		●		◐						◐	
Aquawax 214VF	Oxidized Fischer-Tropsch wax	1.0 - 2.0%	W	I			◐		○		◐		○							
◆ MicroMatte 1213 UVW	Densified modified polypropylene	2.0 - 5.0%	W,S	I	●	◐	◐	○	○		◐		◐	○					◐	
Micropro 400	Modified polypropylene	2.0 - 4.0%	S	E	◐	◐	◐	○	○	◐	◐		○							
MicroTouch Series	Aliphatic polyurethane	2.0 - 8.0%	W	I	●	◐							◐	●		◐	○	◐		
MP-22XF	Fischer-Tropsch wax	1.0 - 2.0%	W,S	I,E			◐		○	◐	◐		○					○		●
◆ MPP-123AL	Polyethylene/Alumina	0.5 - 1.5%	W,S	I,E	◐		●		○		●				◐	○				
NatureFine R331	Rice bran wax	1.0 - 2.0%	W,S	I,E	●	●		○	○		●									●
NatureMatte 31	Poly(hydroxybutyrate-co-hydroxyvalerate)	2.0 - 5.0%	W,S	I,E	●	●	○	○	○				○						◐	●
◆ Polyfluo 190	Polyethylene/PTFE	0.5 - 2.0%	W,S	I,E	◐		●	●	◐		◐		○	○	●					
◆ Polyfluo 900	Ceramic Modified Polyethylene/PTFE	0.5 - 2.0%	W,S	I,E	◐		●	●	◐		●		○	○					●	
PropylMatte 31	Polypropylene	2.0 - 5.0%	W,S	I,E	●	●		◐	◐				○	○					○	
◆ PropylMatte 31HD	Densified polypropylene	2.0 - 5.0%	W	I,E	●	●		◐	◐				○	○					●	
◆ PropylMatte 31SA	Densified polypropylene/PTFE	2.0 - 5.0%	W,S	I,E	●	●		◐	◐				◐	○					●	
PropylTex Series	Polypropylene	3.0 - 10.0%	W,S	I,E	◐	●			◐				◐	○					●	
PropylTex HD Series	Densified polypropylene	3.0 - 10.0%	W	I,E	◐	●						●	◐	○		●			●	
SuperGlide 904	Fischer-Tropsch wax/Ethylene bis(stearamide)	0.5 - 2.0%	S	I			◐	○	◐		●		●	○						
Synfluo 172VF	Fischer-Tropsch wax/PTFE	0.5 - 2.0%	S	I			◐	○	○		●		○						◐	

* W = Water, S = Solvent



MICRO POWDERS, INC.

580 White Plains Road, Tarrytown, NY 10591 | T: 914.793.4058 | micropowders.com | email: mpi@micropowders.com

R-04/20

The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.