

Recommended Products

Typical Properties

(Selector Guide on reverse side)

Product	Melt Point (°C)	Density (g/cc@25°C)	Mean Particle Size (µm)	Max. Particle Size (µm)
AquaBead 519	126 - 132	0.91	6.0 - 8.0	22.00
AquaBead 525E	N/A	1.00	N/A	N/A
AquaKlean 403	N/A	0.98	N/A	N/A
AquaMatte 22	135 - 140	0.99	6.0 - 8.0	22.00
AquaMatte 31	135 - 140	0.99	8.0 - 12.0	31.00
AquaPoly 215VF	105 - 111	0.95	5.0 - 7.5	22.00
AquaPolyfluo 411	117 - 123	1.10	6.0 - 8.0	22.00
Aquawax 214VF	104 - 107	0.96	5.0 - 7.5	22.00
MicroMatte 1213 UVW	150 - 156	1.11	5.0 - 7.5	22.00
Micropro 400	140 - 143	0.93	4.5 - 7.5	22.00
MicroTouch Series	N/A	1.05	Available from 5 µm - 35 µm mean	
MP-22XF	102 - 106	0.94	5.0 - 6.0	22.00
Polyfluo 190	121 - 132	0.99	9.0 - 12.0	31.00
Polyfluo 900	121 - 132	1.02	9.0 - 12.0	31.00
PropylMatte 31	160 - 170	0.86	8.0 - 12.0	31.00
PropylMatte 31HD	160 - 170	1.07	8.0 - 12.0	31.00
PropylMatte 31SA	160 - 170	1.02	8.0 - 12.0	31.00
PropylTex Series	160 - 170	0.89	Wide range available (20 mesh - 325 mesh)	
PropylTex HD Series	160 - 170	1.07	Wide range available (20 mesh - 325 mesh)	
SuperGlide 904	138 - 145	0.97	4.0 - 6.0	22.00
Synfluo 172VF	104 - 110	1.01	4.0 - 7.0	22.00



MICRO POWDERS, INC.
High Performance Wax Additives

Architectural Coatings

The performance demands of today's modern interior and exterior architectural coatings can be achieved with a wax additive that provides effective gloss control, enhanced burnish resistance, improved soil release, and superior in-can stability. Micro Powders products can enhance these properties while also improving water repellency, scratch resistance and adding a smooth surface feel.

Architectural Coatings Selector Guide

● Extremely Effective
 ◐ Very Effective
 ○ Effective

◆ Available as a Waterborne Dispersion

Product	Description	Suggested Use Level	Recommended System Type*	Interior/ Exterior	Burnish Resistance	Mattng and Gloss Control	Block Resistance	Resistance to Dirt Pick Up	Cleanability	Water Repellency/Beading	Scratch and Mar Resistance	Texture	Lubricity and Smooth Feel	Soft Touch	Heel Mark Resistance	Non-Skid	Film Clarity	In-Can Stability	Gloss Retention	
◆ AquaBead 519	Hydrophobically modified synthetic wax	1.0-4.0%	S	E			○	◐	○	●										
AquaBead 525E	Paraffin/carnauba wax emulsion	2.0-10.0%	W	E				◐	○	●								◐		◐
AquaKlean 403	Polyethylene/paraffin wax emulsion	3.0-10.0%	W	I,E	○		◐	◐	●	●								●		●
◆ AquaMatte 22	Oxidized polyethylene	2.0-5.0%	W	I,E	◐	◐	○		◐		●		◐	○					●	
◆ AquaMatte 31	Oxidized polyethylene	2.0-5.0%	W	I,E	◐	●	○		◐		●		◐	○					●	
AquaPoly 215VF	Oxidized polyethylene	1.0-2.0%	W	I			●		○		◐		○							
◆ AquaPolyfluo 411	Modified oxidized polyethylene/PTFE	0.5-2.0%	W	I,E	○		●	○	◐		●		◐						◐	
Aquawax 214VF	Oxidized Fischer-Tropsch wax	1.0-2.0%	W	I			◐		○		◐		○							
◆ MicroMatte 1213 UVW	Densified modified polypropylene	2.0-5.0%	W,S	I	●	◐	◐	○	○		◐		◐	○					◐	
Micropro 400	Modified polypropylene	2.0-4.0%	S	E	◐	◐	◐	○	○	◐	◐		○							
MicroTouch Series	Aliphatic polyurethane	2.0-8.0%	W	I	●	◐					◐		◐	●		◐	○	◐		
MP-22XF	Fischer-Tropsch wax	1.0-2.0%	W,S	I,E			◐		○	◐	◐		○					○		
◆ Polyfluo 190	Polyethylene/PTFE	0.5-2.0%	W,S	I,E	◐		◐	●	◐	◐	◐		○	○	●					
◆ Polyfluo 900	Ceramic Modified Polyethylene/PTFE	0.5-2.0%	W,S	I,E	◐		◐	●	◐	◐	●		○	○					●	
◆ PropylMatte 31	Polypropylene	2.0-5.0%	W,S	I,E	●	●		◐	◐				○	○			○			
◆ PropylMatte 31HD	Densified polypropylene	2.0-5.0%	W	I,E	●	●		◐	◐				○	○			○		●	
◆ PropylMatte 31SA	Polyethylene/PTFE	2.0-5.0%	W,S	I,E	●	●		◐	◐				◐	○					●	
PropylTex Series	Polypropylene	3.0-10.0%	W,S	I,E	◐	●						●		○		●				
PropylTex HD Series	Densified polypropylene	3.0-10.0%	W	I,E	◐	●						●		○		●			●	
SuperGlide 904	Fischer-Tropsch wax/Ethylene bis(stearamide)	0.5-2.0%	S	I			◐	○	◐		●		●	○						
Synfluo 172VF	Fischer-Tropsch wax/PTFE	0.5-2.0%	S	I			◐	○	○		●		○						◐	

* W = Water, S = Solvent



MICRO POWDERS, INC.

580 White Plains Road, Tarrytown, NY 10591 | T:914.793.4058 | micropowders.com | email:mpi@micropowders.com

1-04/18

The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.