



MICRO POWDERS, INC.
High Performance Wax Additives

Industrial Coatings

Coatings for industrial products present a range of performance challenges, from improving slip and lubricity to boosting abrasion resistance and anti-blocking. The right Micro Powders additive can enhance these properties while imparting visual and tactile effects that include mattifying, texturing, and soft touch.

Recommended Products

Typical Properties

(Selector Guide on reverse side)

Product	Melt Point (°C)	Density (g/cc@25°C)	Mean Particle Size (µm)	Max. Particle Size (µm)
AquaMatte 22	135 - 140	0.99	6.0 - 8.0	22.00
AquaPoly 250	117 - 123	0.98	8.0 - 10.0	31.00
AquaPolyfluo 411	117 - 123	1.10	6.0 - 8.0	22.00
AquaPolysilk 19	102 - 118	1.06	9.0 - 11.0	31.00
Fluo HT	>316	2.20	2.0 - 4.0	12.00
Fluo X-1406	>316	2.20	Primary particle size < 0.3 µm	
MicroKlear 116	107 - 113	0.97	4.0 - 5.25	15.56
MicroKlear 709	119 - 124	1.10	4.0 - 6.0	22.00
MicroMatte 1213 UVW	150 - 156	1.11	5.0 - 7.5	22.00
Micropro 440W	150 - 156	0.94	7.0 - 10.0	31.00
Micropro 500	141 - 143	0.94	4.5 - 7.5	22.00
Microspersion 526E	N/A	1.00	N/A	N/A
MicroTouch Series	N/A	1.05	Available from 5 µm - 35 µm mean	
MP-22XF	102 - 106	0.94	5.0 - 6.0	22.00
MPP-620VF	114 - 116	0.95	5.0 - 7.0	22.00
MPP-620XF	114 - 116	0.95	4.5 - 5.5	22.00
NyloTex Series	218 - 224	1.14	Wide range available (20 mesh - 200 mesh)	
Polyfluo 150	113 - 116	1.15	3.5 - 5.5	15.56
Polyfluo 190	121 - 132	0.99	9.0 - 12.0	31.00
Polyfluo 523XF	113 - 117	1.26	3.5 - 5.5	15.56
Polyfluo 900	121 - 132	1.02	9.0 - 12.0	31.00
Polysilk 14	96 - 118	1.04	7.5 - 9.5	31.00
PropylMatte 31	160 - 170	0.86	8.0 - 12.0	31.00
PropylMatte 31HD	160 - 170	1.07	8.0 - 12.0	31.00
PropylMatte 31SA	160 - 170	1.02	8.0 - 12.0	31.00
PropylTex Series	160 - 170	0.89	Wide range available (14 mesh - 325 mesh)	
PropylTex HD Series	160 - 170	1.07	Wide range available (200 mesh - 325 mesh)	
Superslip 6515	124 - 137	0.95	6.0 - 8.0	22.00
Synfluo 178VF	104 - 110	1.03	4.0 - 7.0	22.00

Industrial Coatings

Selector Guide

● Extremely Effective ◐ Very Effective ○ Effective

💧 Available as a Waterborne Dispersion

Product	Description	Suggested Use Level	Recommended System Type*	Scratch & Abrasion Resistance	Burnish Resistance	Metal Mark Resistance	Apparent Hardness	Slip and Lubricity	Block Resistance	Increased COF	Matting & Gloss Control	Texture	Soft Touch	Heat Resistance	Early Water Resistance	Gloss Retention
💧 AquaMatte 22	Oxidized polyethylene	2.0-5.0%	W	●	○		●	◐	○		◐					
💧 AquaPoly 250	Modified oxidized polyethylene	0.5-2.0%	W	◐	○	◐	◐	◐	○							
💧 AquaPolyfluo 411	Modified oxidized polyethylene/PTFE	0.5-2.0%	W	●	◐	●	◐	◐	◐					○		
💧 AquaPolysilk 19	Modified oxidized polyethylene/PTFE	0.5-2.0%	W	●	◐		◐	●	●					○		
💧 Fluo HT	Polytetrafluoroethylene (PTFE)	0.5-2.0%	W,S	●	○		○	◐						●		○
💧 Fluo X-1406	Submicron spherical PTFE	0.5-1.0%	W,S	◐	○		○	◐						●	○	●
MicroKlear 116	Polyethylene/carnauba wax	1.0-3.0%	W,S	◐	○		◐	●	●						○	◐
MicroKlear 709	PTFE modified polyethylene/carnauba wax	1.0-3.0%	W,S	●	◐		●	●	●						○	
💧 MicroMatte 1213 UWV	Densified modified polypropylene	1.0-5.0%	W,S	◐	●	○	○	○	◐		◐				○	
💧 Micropro 440W	Modified polypropylene	1.0-5.0%	W,S	◐	◐	○	○	○	◐		◐					
Micropro 500	Modified polypropylene	1.0-5.0%	W,S	◐	◐	○	◐	◐	◐		◐				◐	
Microspersion 526E	Polyethylene wax emulsion	3.0-6.0%	W	○	○		○	◐	○							●
MicroTouch Series	Aliphatic polyurethane	4.0-8.0%	W,S		●					◐	◐	○	●			
💧 MP-22XF	Fischer-Tropsch wax	1.0-3.0%	W,S	◐	○		○	◐	○						◐	
💧 MPP-620VF/XF	High density polyethylene	1.0-3.0%	W,S	◐	◐	◐	◐	◐	○							○
NyloTex Series	Polyamide (Nylon 6)	4.0-6.0%	W,S	●					◐	◐		●	○	◐		
💧 Polyfluo 150	Polyethylene/PTFE	0.5-3.0%	W,S	◐	◐		●	●	◐							◐
💧 Polyfluo 190	Polyethylene/PTFE	0.5-3.0%	W,S	●	●	●	◐	○	◐		○					
💧 Polyfluo 523XF	Polyethylene/PTFE	0.5-3.0%	W,S	●	◐		●	●	◐					○		◐
💧 Polyfluo 900	Ceramic modified polyethylene/PTFE	0.5-3.0%	W,S	●	●	●	●	○	◐		○			○		
Polysilk 14	Modified polyethylene/PTFE	0.5-2.0%	W,S	◐	◐		◐	●	●				◐			
PropylMatte 31	Polypropylene	2.0-5.0%	S		●				○	◐	●					
💧 PropylMatte 31HD	Densified polypropylene	2.0-5.0%	W		●				◐	◐	●					
💧 PropylMatte 31SA	Densified polypropylene/PTFE	2.0-5.0%	W,S	●	●			◐	◐		●					
PropylTex Series	Polypropylene	3.0-10.0%	S		◐				◐	●	◐	●	○			
PropylTex HD Series	Densified polypropylene	3.0-10.0%	W		◐				◐	●	◐	●	○			
Superslip 6515	Polyethylene/Ethylene bis(stearamide)	1.0-3.0%	W,S	◐	◐		○	●	●				○		○	◐
Synfluo 178VF	Fischer-Tropsch wax/PTFE	0.5-3.0%	W,S	◐	○		◐	●	◐							◐

* W = Water, S = Solvent