



MICRO POWDERS, INC.
High Performance Wax Additives

Wood Coatings

The natural beauty of a coated wood surface can be protected and enhanced with additives that improve scratch and mar resistance, add lubricity, and impart a smooth surface feel. Micro Powders products can enhance these properties while providing texture, gloss reduction, water beading, and more.

Recommended Products Typical Properties

(Selector Guide on reverse side)

Product	Melt Point (°C)	Density (g/cc@25°C)	Mean Particle Size (µm)	Max. Particle Size (µm)
AquaBead 270E	N/A	0.96	N/A	N/A
AquaBead 519	126 - 132	0.91	6.0 - 8.0	22.00
AquaBead 525E	N/A	1.00	N/A	N/A
AquaMatte 22	135 - 140	0.99	6.0 - 8.0	22.00
AquaPoly 215	105 - 111	0.95	9.0 - 11.0	31.00
AquaPolyfluo 411	117 - 123	1.10	6.0 - 8.0	22.00
AquaSuperslip 6550	124 - 135	0.94	6.0 - 7.5	22.00
Aquawax 214VF	104 - 107	0.96	5.0 - 7.5	22.00
MicroMatte 1213 UVW	150 - 156	1.11	5.0 - 7.5	22.00
Micropro 400	140 - 143	0.93	4.5 - 7.5	22.00
Micropro 440W	150 - 156	0.94	7.0 - 10.0	31.00
Micropro 500	141 - 143	0.94	4.5 - 7.5	22.00
Micropro 700	149 - 154	1.04	5.0 - 7.0	22.00
MicroTouch 800XF	N/A	1.05	7.0 - 9.0	31.00
MicroTouch 850XF	N/A	1.02	5.0 - 8.0	31.00
MP-22XF	102 - 106	0.94	5.0 - 6.0	22.00
MPP-620VF	114 - 116	0.95	5.0 - 7.0	22.00
NyloTex Series	218 - 224	1.14	Wide range available (20 mesh - 200 mesh)	
Polyfluo 540	108 - 115	1.02	5.0 - 6.0	22.00
Polyfluo 900	121 - 132	1.02	9.0 - 12.0	31.00
PropylMatte 31	160 - 170	0.86	8.0 - 12.0	31.00
PropylMatte 31HD	160 - 170	1.07	8.0 - 12.0	31.00
PropylMatte 31SA	160 - 170	1.02	8.0 - 12.0	31.00
PropylTex Series	160 - 170	0.89	Wide range available (20 mesh - 325 mesh)	
PropylTex HD Series	160 - 170	1.07	Wide range available (200 mesh - 325 mesh)	
SuperGlide 904	138 - 145	0.97	4.0 - 6.0	22.00
Superslip 6515	124 - 137	0.95	6.0 - 8.0	22.00
Superslip 6530	124 - 135	0.95	5.5 - 7.5	22.00
Synfluo 178VF	104 - 110	1.03	4.0 - 7.0	22.00
Synfluo 180XF	104 - 110	1.10	3.0 - 5.0	11.00

Wood Coatings Selector Guide

● Extremely Effective ● Very Effective ○ Effective

💧 Available as a Waterborne Dispersion

Product	Description	Suggested Use Level	Recommended System Type*	Scratch & Mar Resistance	Lubricity & Smooth Feel	Soft Touch	Block Resistance	Matting & Gloss Control	Burnish Resistance	Texture	Water Repellency/beading	Sanding Efficiency	Gloss Retention	Clarity
AquaBead 270E	Paraffin wax emulsion	3.0-10.0%	W								●		○	○
💧 AquaBead 519	Hydrophobically modified synthetic wax	1.0-4.0%	W,S								●			
AquaBead 525E	Paraffin/carnauba wax emulsion	2.0-10.0%	W								●		●	○
💧 AquaMatte 22	Oxidized polyethylene	2.0-5.0%	W	●				●	●					
💧 AquaPoly 215	Oxidized polyethylene	0.5-2.0%	W	●	●		●							
💧 AquaPolyflu 411	Modified oxidized polyethylene/PTFE	0.5-2.0%	W	●	●		●						●	○
💧 AquaSuperslip 6550	Modified oxidized polyethylene/amide	0.5-2.0%	W	●	●		●					●		
Aquawax 214VF	Oxidized Fischer-Tropsch wax	0.5-2.0%	W	●	●									
💧 MicroMatte 1213 UVW	Densified modified polypropylene	2.0-4.0%	W,S				●	●	●					
Micropro 400	Modified polypropylene	2.0-4.0%	W,S	●			●	●	●		●	○		
💧 Micropro 440W	Modified polypropylene	2.0-5.0%	W	●			●	●	●					
Micropro 500	Modified polypropylene	2.0-4.0%	W,S	●			●	●	●			○		
Micropro 700	Modified polypropylene/PTFE	0.5-4.0%	W,S	●	●		●	●	●					
MicroTouch 800XF	Aliphatic polyurethane	1.0-10.0%	W,S	●		●		●						
MicroTouch 850XF	Modified aliphatic polyurethane	1.0-10.0%	W,S	●		●		●						
MP-22XF	Fischer-Tropsch wax	1.0-3.0%	W,S	○	○						●		●	
💧 MPP-620VF	High density polyethylene	0.5-1.5%	W,S	●									●	●
NyloTex Series	Polyamide (Nylon 6)	4.0-6.0%	W,S							●				
Polyflu 540	Polyethylene/PTFE	0.5-1.0%	W,S	●	●								●	●
Polyflu 900	Ceramic modified polyethylene/PTFE	1.0-3.0%	W,S	●			○	●	●					
💧 PropylMatte 31	Polypropylene	1.0-5.0%	S			○	●	●	●			○		
💧 PropylMatte 31HD	Densified polypropylene	1.0-5.0%	W			○	●	●	●					
💧 PropylMatte 31SA	Densified polypropylene/PTFE	1.0-5.0%	W,S	●	●	○	●	●	●					
PropylTex Series	Polypropylene	3.0-10.0%	S			○		●		●				
PropylTex HD Series	Densified Polypropylene	3.0-10.0%	W			○		●		●				
SuperGlide 904	Fischer-Tropsch wax/Ethylene bis(stearamide)	0.5-3.0%	W,S		●	●	●		●			●	●	
Superslip 6515	Polyethylene/Ethylene bis(stearamide)	0.5-3.0%	W,S		○		●		●			●	●	
Superslip 6530	Polyethylene/Ethylene bis(stearamide)	0.5-3.0%	W,S		●		●		●			●	●	
Synflu 178VF	Fischer-Tropsch wax/PTFE	0.5-2.0%	W,S	●	●								●	●
Synflu 180XF	Fischer-Tropsch wax/PTFE	0.1-0.3%	W,S	●	●								●	○

* W = Water, S = Solvent



MICRO POWDERS, INC.

580 White Plains Road, Tarrytown, NY 10591 | T:914.793.4058 | micropowders.com | email:mpi@micropowders.com

1-04/18

The information contained herein is to the best of our knowledge true and correct and any suggestions are made without guarantee, express or implied, since conditions of use are beyond our control. Micro Powders, Inc. disclaims any liability incurred in connection with the use of any data or suggestions. Nothing contained herein shall be construed as a recommendation to infringe on any existing patents covering any material or its use.